# Coating, Kneading and Reactive Types

# Antistatic Agents for Synthetic Resins

### **Preface**

Synthetic resins have high insulation resistance and their surfaces easily become charged with static electricity. Therefore, the static electricity in synthetic resins often causes problems. For example, dust spoils the beauty of synthetic resins due to static adhesion. Moreover, static electricity interferes in plastic production processes, and causes other problems such as the destruction of electronic circuits, electrical shock, and malfunction of appliances. We offer a wide range of antistatic agents for synthetic resins in accordance with the kind of resins applied and production process to prevent such electrostatic hazard.

	Uses for Applications							
	Kneading (for polymer alloy)					Coating	Reactive	Registry No.
Product Name	Polyolefin	Polyvinyl chloride	Polyester	ABS resins	Various inks	Various resins	Polyamide	Identified by Positive List System*
CHEMISTAT 3033	А	А	А	А	-	-	-	[B]NM-3184
CHEMISTAT 3500	-	_	_	_	А	-	-	_
CHEMISTAT Y-400	-	-	-	_	-	-	A	_

# <Lists of CHEMISTAT and SANSTAT products>

A : Applicable, \* The Japan Hygienic Olefin and Styrene Plastics Association Provides it.

We offer a wide range of permanent antistatic agents as antistatic additives under the trade name of PELESTAT and PELECTRON.



**Typical Properties** 

# 1. Typical Properties

Tables 1-a and 1-b show the typical properties and features of antistatic agents for synthetic resins. The values are representative.

Product Name	Appearance	lonic	Solids Content wt %	Melting Point* °C
CHEMISTAT 3033	Pale yellow colored granule to flake	Anionic	99	70 *
CHEMISTAT 3500	Pale yellow paste	Anionic	97	-
CHEMISTAT Y-400	Straw-colored granule	Nonionic	98	55

Table 1-a. Typical Properties	Table 1-a.	Typical Properties
-------------------------------	------------	--------------------

\*Softening point

#### Table 1-b. Features

Product Name	Features		
CHEMISTAT 3033	Excellent heat resistance. Effective when used with resins having a high Tg (inappropriate for transparent products).		
CHEMISTAT 3500	Applicable to inks and paints.		
CHEMISTAT Y-400	Reactive type (copolymerized as a component of polyamide **) Imparts flexibility besides antistatic property.		

\*\* Polyoxyethylene diaminopropylether (total of amine values: approx. 25)



# 2. Heat Resistance

Figure 1 shows the TG curve of CHEMISTAT 3033.



Figure 1. TG curve

Testing method:

Thermogravimetric analyzer (heating rate: 10 °C/min), in an atmosphere of nitrogen.



#### Performances

The following test data shows antistatic properties of each antistatic agent as well as the relationship between humidity and antistatic properties, etc.

Antistatic properties depend on the kind of resin, reaction method, kneading method, coating method, molding conditions of the resin, etc.

1. Relationship Between the Amount of Kneading Type Antistatic Agents and the Surface Resistivity Figure 2 shows the relationship between the amount of kneading type antistatic agents, CHEMISTAT 3033 in polypropylene (PP) and the surface resistivity.



Figure 2. Relationship between Amount of Kneading Type Antistatic Agents and Surface Resistivity

Materials and Method:

Materials:

A predetermined amount of the antistatic agent as described in Figure 2 and PP were blended, and the mixture was kneaded with a Henschel mixer. The kneaded mixture was then molded with an injection molding machine [injection temperature: approx. 225 °C, injection pressure: 8MPa (gauge), molding temperature: 40 °C] into plate type samples (80 mm×80 mm×2 mm). These samples were kept at 20 °C, 65% R.H. for 1 week.

Method:

The surface resistivity of each sample was measured at 20 °C, 65% R.H. using an ultramegohmmeter.



2. Relationship Between the Amount of Reactive Type Antistatic Agent and the Surface Resistivity Figure 3 shows the relationship between the amount of reactive type antistatic agent in polyamide and the surface resistivity. Approx. 20 wt % of CHEMISTAT Y-400, copolymerized with polyamide, exhibits an excellent antistatic property.



Amount of Antistatic Agent Copolymerized (wt %)

Figure 3. Relationship Between Amount of Reactive Type Antistatic Agents and Surface Resistivity

Materials and Method:

Materials:

A predetermined amount of CHEMISTAT Y-400 as described in Figure 3, adipic acid having an identical amount of substance concentration (mole) to CHEMISTAT Y-400, and the required amount of  $\epsilon$ - caprolactam\* were copolymerized with polyamide, and pellets were made. The pellets were molded using a press at 200 °C, 30 MPa for 3 min into sheets 500 µm in thickness. They were then kept at 20 °C, 65%R.H. for 1 week, and used for samples.

Method:

See Figure 2.

\* To achieve the amount of copolymerized CHEMISTAT Y-400 with polyamide as described in Figure 4.



3. Relationship Between the Amount of Antistatic Agents for Inks and the Surface Resistivity

Figure 4 shows the relationship between the amount of CHEMISTAT 3500, added to a commercially available gravure ink, and the surface resistivity.

Approx. 1 wt % of CHEMISTAT 3500 (for ink resin content) inhibits both ink blots caused by static electricity and ink-scattering.



Amount of Antistatic Agent Blended (wt %)

Figure 4. Relationship Between Amount of Antistatic Agents and Surface Resistivity

# Materials and Method:

Materials: A predetermined amount of CHEMISTAT 3500 as described in Figure 4 was blended with commercially available gravure ink (Each proportion of CHEMISTAT 3500 to the ink resin content

is described in Figure 5.). Dried PP films were coated with ink at 2  $\mu$ m in thickness, and dried. They were then kept at 20 °C, 65%R.H. for 24 hours.

#### Method:

See Figure 2.



#### Application Methods

# 1. Recommended Amount

The amount of antistatic agents to be applied depends on the performance requirements, the kind of resin and the molded form, however, the standard amount is as follows:

Compounding Mathad	Molded Form			
Compounding Method	Molded Material	Film, Sheet		
Kneading	1 – 2 wt %	0.3 – 1 wt %		
Coating	0.05 – 0.1 g/m <sup>2</sup>			
Reactive	2 – 10 wt % (CHEMISTAT Y-400)			

Table 3.	Standard Amount
Table 3.	Stanuaru Amouni

#### 2. Compounding Method

#### Kneading

- There are two different methods
- $\cdot$  Mix antistatic agents into pellets or powder to achieve the required concentration, using a blender.
- Produce master batches which contain a higher concentration of antistatic agents beforehand, and then mix them into pellets or powder to achieve the required concentration.

Recommended mixer: Henschel mixer

#### Coating

• Dilute antistatic agents with water to achieve the required concentration, coat resins with them using the brief immersion method, or a spray coater or a roll coater, and then dry the coated resins.

Reactive

The composition of CHEMISTAT Y-400 is polyoxyethylene diaminopropylether (total of amine values: approx. 25). Refer to Figure 4 on page 6, CHEMISTAT Y-400 should be copolymerized with polyamide as a component of polyamide.

# Precautions Against Mishandling

- Too much additive amount of antistatic agents may have a negative effect on the resin's physical properties such as defective moldings/stickiness. Test the effect on their physical properties beforehand to ensure that there are no problems.
- · Use these products under optimal conditions after studying kneading, coating, reactive methods, etc.
- Seal these products closely under moisture-proof conditions after use because they have some hygroscopic properties.



# Important :

Before handling these products, refer to the Safety Data Sheet for recommended protective equipment, and detailed precautionary and hazards information.

This brochure has been prepared solely for information purposes. Sanyo Chemical Industries, Ltd. extends no warranties and makes no representations as to the accuracy or completeness of the information contained herein, and assumes no responsibility regarding the suitability of this information for any intended purposes or for any consequences of using this information. Any product information in this brochure is without obligation and commitment, and is subject to change at any time without prior notice. Consequently anyone acting on information contained in this brochure does so entirely at his/her own risk. In particular, final determination of suitability of any material described in this brochure, including patent liability for intended applications, is the sole responsibility of the user. Such materials may present unknown health hazards and should be used with caution. Although certain hazards may be described in this brochure, Sanyo Chemical Industries, Ltd. cannot guarantee that these are the only hazards that exist.

For detailed information, please contact below. Head Office & Research Laboratory of Sanyo Chemical Industries, Ltd. Address: 11-1, Ikkyo Nomoto-cho, Higashiyama-ku, Kyoto 605-0995, Japan Tel: +81-75-541-4311 Fax: +81-75-551-2557



Tokyo Branch Office of Sanyo Chemical Industries, Ltd. E-mail: sanyoproduct@sanyo-chemical.group Address: 24th Fl., Hibiya Fort Tower, 1-1-1, Nishi-shimbashi, Minato-ku, Tokyo 105-0003, Japan Tel: +81-3-3500-3411 Fax: +81-3-3500-3412 URL https://www.sanyo-chemical.co.jp/eng

